


## Neo Color

**FOR PROFESSIONAL USE ONLY**

### Description

Neo Color is a primer surfacer designed for vehicle refinishes, with high corrosion resistance and can also be used as sanding or non sanding primer surfacer. It is a colored primer system consists of 4 different colors, that are also intermixable. Neo Color is suitable for steel, galvanized steel and aluminum surfaces and contributes to the topcoat coverage with different color components.

### Sanding version



4 Akripol Neo Color  
1 Akripol 2K Hardeners  
1 Akripol Universal Acrylic Thinners




Spray gun set-up:  
1.6 – 1.8 mm

Application pressure:  
1.7-2.2 bar at the spray gun air inlet  
HVLP max 0.6-0.7 bar at the air cap



2 – 3 coats



Between coats:  
5 - 10 minutes at 20°C

Before curing:  
5 - 10 minutes at 20°C



2.5 hours at 20°C

30 minutes at 60°C




Use suitable respiratory protection  
Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator

Read complete TDS for detailed product information

## Neo Color

FOR PROFESSIONAL USE ONLY

### Non Sanding version



3 Neo Color  
1 Akripol 2K Hardener Slow  
1 Akripol Universal Acrylic Thinners




Spray gun set-up:  
1.3 mm

Application pressure:  
1.7-2.2 bar at the spray gun air inlet  
HVLP max 0.6-0.7 bar at the air cap



1 coat



Flash-off time:  
15 minutes at 20°C

Recoat within:  
24 hours at 20°C



Recoatable with all AkzoNobel Kemipol basecoats and 2K topcoats



Use suitable respiratory protection  
Akzo Nobel Car Refinishes recommends to use of a fresh air supply respirator

## Neo Color

**FOR PROFESSIONAL USE ONLY**

### Description

Neo Color is a primer surfacer designed for vehicle refinishes, with high corrosion resistance and can also be used as sanding or non sanding primer surfacer. It is a colored primer system consists of 4 different colors, that are also intermixable. Neo Color is suitable for steel, galvanized steel and aluminum surfaces and contributes to the topcoat coverage with different color components.

### Product and Additives

	Neo Color
<b>Hardener</b>	Akripol 2K Hardener Extra Fast / Fast / Slow
<b>Thinner</b>	Akripol Universal Acrylic Thinner Fast / Slow

### Raw Materials

Neo Color:	Acrylic Resins
Akripol 2K Hardener:	Polyisocyanate Resins

### Suitable Substrates

Existing finishes  
Steel  
Galvanized steel  
Aluminum  
Polyester surfaces  
Washprimer 1K CF  
Akripol Bodyfillers

### Substrate Preparation



**Substrate cleaning:** Before sanding, clean with suitable substrate cleaners to remove possible contaminations from the substrate. Wash the substrate with warm water and detergent beforehand and rinse thoroughly.



**Existing finishes:**  
Degrease and dry sand with P280 grit or wet sand with P400 grit.

**Polyester Putties:**  
Dry sand with P280.



**Steel surfaces:**  
Degrease and dry sand with P120-220 grit.



**Substrate cleaning:** Before applying, clean the surface by using suitable surface cleaning thinner to remove possible impurities.

## Neo Color


FOR PROFESSIONAL USE ONLY

### Mixing before application



Stir Akripol Neo Color until homogeneous before use.

### Mixing Ratio by Volume




#### Sanding version

4 parts Akripol Neo Color  
1 part Akripol 2K Hardeners  
1 part of Akripol Universal Acrylic Thinners

#### Non Sanding version

3 parts Akripol Neo Color  
1 part Akripol 2K Hardener Slow  
1 part Akripol Universal Acrylic Thinners

### Viscosity



#### Sanding version

20 seconds at 20°C (DIN4)

#### Non Sanding version

18 seconds at 20°C (DIN4)

### Spray gun fluid tip / Working pressure



#### Sanding version

**Spray Gun**  
Gravity feed

**Fluid Tip**  
1.6-1.8 mm

#### Application Pressure

1.7 – 2.2 bar at spray gun the air inlet  
HVLP max. 0.6-0.7 bar at the air-cap

#### Non Sanding version

**Spray Gun**  
Gravity feed

**Fluid Tip**  
1.3 mm

#### Application Pressure

1.7 – 2.2 bar at spray gun the air inlet  
HVLP max. 0.6-0.7 bar at the air-cap

### Pot-life

#### Sanding version

60 mins after mixing at 20°C with Akripol 2K Hardener Fast

#### Non Sanding version

45 mins after mixing at 20°C with Akripol 2K Hardener Fast

## Neo Color

**FOR PROFESSIONAL USE ONLY**


### Application process



Sanding version  
Apply 2-3 single coats, allowing for 5-10 minutes flash-off time between coats.

Non Sanding version  
Apply 1 single coat, allowing for at least 15 minutes flash-off time before any application.

### Drying time



	Dry sanding		Wet sanding	
	20°C	60°C	20°C	60°C
Fast hardener	3 hours	30 min.	3 hours	30 min.
Extra fast hardener	2.5 hours	30 min.	2.5 hours	30 min.

### Final sanding



Final sanding step P500



Final sanding step P1000



Remove contamination using an appropriate cleaner

### Recoatable with

All AkzoNobel Kemipol basecoats and 2K topcoats.

### Film thickness

~50 µm film per coat (sanding version)

~25 µm film per coat (non sanding version)

### Theoretical material usage

Sanding version  
The theoretical material usage is 8 m<sup>2</sup>/l. at 50 µm (ready to spray mixture).

Non Sanding version  
The theoretical material usage is 16.4 m<sup>2</sup>/l. at 25 µm (ready to spray mixture).

Note : The practical material usage depends on many factors i.e. shape of the object, roughness of the surface, application method and application circumstances.

# Neo Color

**FOR PROFESSIONAL USE ONLY****Cleaning of equipment:**

Akrisol Super Cellulosic Thinner

**Product storage**

Product shelf-life is determined when products are stored unopened at 20°C.  
Avoid extreme temperature fluctuation.



AkzoNobel Kemipol  
Kemalpaşa OSB Mahallesi İzmir - Ankara Yolu  
Ansızca Küme Evleri No:287  
35730, Kemalpaşa - İzmir / Türkiye  
T: +90 232 877 00 30

**HEALTH & SAFETY DATA concerning Neo Color and additives:**

For professional use only.(See Material Safety Data Sheet). See text on the label of this product. The user of this product is required to comply with the national statutory regulations for health and safety at work and waste disposal.

The effectiveness of our systems is based on laboratory research and many years' practical experience. We guarantee that the quality of the work performed according to our system meets the AKZONOBEL KEMİPOL A.Ş standards, provided that our instructions are carefully followed and the work is performed in accordance with the requirements as to good craftsmanship. We decline any responsibility if the final result is affected by factors beyond our control. The customer has to determine the suitability of the delivered products for the intended application by using the means which normally are at his disposal.

[www.akripol.com.tr](http://www.akripol.com.tr)

**AKZONOBEL KEMİPOL A.Ş. İzmir, TÜRKİYE**