


Puttymaster

FOR PROFESSIONAL USE ONLY

Description	
Two-pack polyester putty designed with easy application and high build properties to fill dents and surface irregularities in body parts made of steel, galvanized steel and aluminum.	
	100 Puttymaster 2 AkzoNobel Putty Hardener
	Application time: 5-8 minutes at (20°C)
	30 minutes at (20°C)
	Final sanding step for bodyfiller P180 - P220
	Final sanding step for featheredge P320 - P400
	Recoatable with any Akripol preparatory product
	Use suitable respiratory protection Akzo Nobel Car Refinishes recommends the use of a fresh air supply respirator.

Read complete TDS for detailed product information

Puttymaster

FOR PROFESSIONAL USE ONLY

Description

Two-pack polyester putty designed with easy application and high build properties to fill dents and surface irregularities in body parts made of steel, galvanized steel and aluminum.

Preparation process



Remove any surface contamination prior to sanding application using appropriate surface cleaner.
Pre-clean the surface with warm water and detergent, rinse sufficiently with clean water.



Remove existing coating and sand down to the bare substrate using P180 - P220 grit as the final step.



Remove any surface contamination prior to putty / bodyfiller application using appropriate surface cleaner.

Suitable substrates

Steel
 Galvanized Steel
 Aluminum
 Polyester surfaces
 AkzoNobel Kemipol Epoxy primers
 Note: Do not apply Puttymaster onto thermoplastic acrylic finishes and Washprimer 1K CF.


Products and additives

Puttymaster
 AkzoNobel Putty Hardener

Basic raw materials

Puttymaster: Polyester resins
 Hardener: Peroxide

Mixing



100 parts Puttymaster
2 parts AkzoNobel Putty Hardener

Mix the bodyfiller thoroughly to a homogeneous mass (uniform colour).
Avoid air entrapment.
Mix the correct amount by weight (on a scale).

Puttymaster

FOR PROFESSIONAL USE ONLY

Pot-life

Application time 5-8 minutes at (20°C).


Application



Apply the polyester bodyfiller to the bare substrate by placing the spreader at a 60° angle. Avoid thick edges of bodyfiller around the perimeter of the repair by tapering away toward the original finish.

- Do not apply Puttymaster directly to any existing finishes or directly on top of any acid containing washprimer.
- Systems demanding the highest corrosion resistance should be applied over Epoxy primer.
- Application temperature range between 15°C-35°C.

Drying



Ready to sand after 30 minutes at 20°C.
If force dried, the bodyfiller can be sanded after 15 minutes at 40°C.



Ready to sand after 4 minutes.
Use IR **low** power setting at a 50-70 cm distance between panel and IR unit.
Temperature should not exceed 90°C.

Sanding process



P80 - P120 - P220
Use a guide coat between the sanding steps.



P220 - P320 (P400 for a spot repair).
Take care to remove any coarse sanding scratches that may have been created in the feather edge area during the sanding of the bodyfiller.



Remove any surface contamination prior to filler / surfacer application using appropriate surface cleaner.
Where bodyfiller is exposed, avoid contact with water (e.g. waterborne degreaser).

Puttymaster

FOR PROFESSIONAL USE ONLY**Recoatable with**

All current Akripol preparatory products with the exception of waterborne products.

Cleaning of equipment

Akripol Super Cellulosic Thinner

Product storage

Product shelf-life is determined when products are stored unopened at 20°C.

Avoid extreme temperature fluctuation.

- *Product shelf life data see TDS S9.01.02*

AkzoNobel Kemipol
Kemalpaşa OSB Mahallesi İzmir - Ankara Yolu
Ansızca Küme Evleri No:287
35730, Kemalpaşa - İzmir / Türkiye
T: +90 232 877 00 30

HEALTH & SAFETY DATA concerning Akripol Puttymaster and additives:

For professional use only.(See Material Safety Data Sheet). See text on the label of this product. The user of this product is required to comply with the national statutory regulations for health and safety at work and waste disposal.

The effectiveness of our systems is based on laboratory research and many years' practical experience. We guarantee that the quality of the work performed according to our system meets the AKZONOBEL KEMİPOL A.Ş standards, provided that our instructions are carefully followed and the work is performed in accordance with the requirements as to good craftsmanship. We decline any responsibility if the final result is affected by factors beyond our control. The customer has to determine the suitability of the delivered products for the intended application by using the means which normally are at his disposal.

www.akripol.com.tr

AKZONOBEL KEMİPOL A.Ş. İzmir, TÜRKİYE